

# 第 121 回 マテリアル セミナー

下記日程で第 121 回マテリアルセミナーを開催いたします。多数ご参加下さい。

題目: **Additive Manufacturing of structural and piezoelectric ceramics**

講師: **Prof. Dariusz Kata,**

AGH University of Science and Technology, Cracow, Poland

日時: 平成 30 年 8 月 31 日(金) 16:00~17:00

場所: 北大工学部 材料・化学棟 1 階 中会議室 (MC 1 0 2)

連絡先: 北大 材料科学部門 松浦清隆 ([matsuura@eng.hokudai.ac.jp](mailto:matsuura@eng.hokudai.ac.jp), 011-706-6343)

## Abstract

Additive Manufacturing (AM) is widely known and appreciated due to its flexible and customized manufacturing capabilities. Today, the AM technology has contributed to almost all engineering areas that include mechanical, materials, industrial, aerospace, electrical and most recently biomedical engineering. It is also very useful to manufacture and shaping of structural and piezoelectric ceramics. The applicability of AM is shown by appropriate assessment based on the three material systems, namely: (1) AlN-graphene nanocomposite; (2) Inconel 625 – WC composite and (3) KNN (K<sub>0.5</sub>Na<sub>0.5</sub>)NbO<sub>3</sub> solid solution.

The anisotropic AlN-graphene nanocomposites were shaped by AM technology. The structures, morphologies, and microstructures of those hybrids were examined by X-ray diffraction, SEM and TEM methods. It is showed that additive manufacturing significantly influenced on thermal anisotropy and microstructure appearance. The results were correlated with thermal conductivity of the samples carried out by the laser pulse method - LFA 427 apparatus. The possibility of controlling anisotropy by graphen content and Additive Manufacturing conditions is showed.

Chemically and structurally homogenous Inconel 625 – WC composite coatings were prepared by Additive Manufacturing. Because of chemical composition of Inconel 625 superalloy, secondary carbides of WC, W<sub>2</sub>C, NbC, (NbW)C, W<sub>6</sub>C<sub>2.54</sub> and (W,Cr,Ni)<sub>23</sub>C<sub>6</sub> were detected in the intergranular spaces by XRD analysis. They appeared in form of eutectic with typical fishbone-like structure in samples containing increased amount of WC - 30 wt %. High cooling rate during AM was the reason of fine microstructure in produced material. TEM observation showed two types of precipitations: angular carbides and spherical oxides containing increased amount of Cr, Si and Ti.

The Additive Manufacturing is very perspective technology for providing wireless power supply to transducers in low-energy measurement, signal or control systems. The KNN piezoelectric generators have a wide application potential in this regard. However it is very difficult to obtain dense sinters from the KNN solid solutions. On one hand, their phase stability is limited to the temperatures (1040°C for potassium niobate and 1140°C for KNN) which significantly limit the sintering process. In addition, small changes in stoichiometry, both towards the potassium and niobium, can lead to creation of a number of phases in which the stoichiometry is different than the stoichiometry corresponding to the perovskite, and this has a significant adverse impact on the level of dielectric losses. However, by applying AM technology, KNN remains the most important candidate to replace the lead-containing materials.

The fundamental interaction of AM laser beam and KNN was examined. Thus the laser sintering and welding process was perform to shape different forms of transducers. Laser processing parameters, microstructure, and features of joined layer, are illustrated. The different aspects of the ceramic laser processing from fundamental mechanism up to engineering applicability is discussed.